

Testing project	Value
Density	22.3
Tensile Strength, MPa	80.6
Elongation at Rupture, %	2.1
Modulus of Elasticity, MPa	2636
Impact Strength, kJ/m <sup>2</sup>	18.1
Vicat Softening Point, °C	137
Residual Shrinkage, %	2
Deflection Temperature, °C	102
Coefficient of Linear Thermal Expansion (0°C — +50°C), °C <sup>-1</sup>	7.4*10 <sup>-5</sup>
Rockwell Hardness (M)	101
Sound Reduction Index, dB	34
Light Transmittance, %	90